



CAPAGEL FLEX COLOR 3-12

Deformable Mortar For 3-12mm Joints

Description

CAPAGEL FLEX COLOR 0-5 12 is a gel grout, whose benefits are those of a cement-based tile grout classified according to UNE EN 13888 as CG2 WA.

High color strength and resistance. Great waterproofing power. Easy to apply and clean. Besides, the “stop powder” ensures the health at work by reducing around 95% the air-suspended powder emission. It comes in a range of 30 colors.

It is an antibacterial tile grout and a natural fungicide. Eco- friendly and recyclable. Suitable for indoor and outdoor use, in swimming pools, glass mosaic “Gresitte”. Very low emissions of volatile organic compounds (VOC). Its special composition allows you to obtain a higher product yield, by consuming less kg per m² of application.

Advantage

- CAPAGEL technology
- Reduced consumption
- Increased yield
- Stop powder
- Full application warranty
- Eco-friendly

Technical Data

Application Data:

Mixing water	From 23 to 24%
Mixture time	≥ 90min
Ambient temperature, application surface and materials	From +5°C to +35°C
Joint width	From 0 to 5mm
Correction time at +23°C	≥ 20 min
Open time to +23°C	≥ 60 min

Passability	+23°C approx. 12h +5°C approx. 50h
Putting into service at +23°C	Light traffic after approx. 2 days Heavy traffic after approx. 3 days

Performance Data:

Flexural strength at 28 days	≥ 6.75 N/mm ²
Compressive strength at 28 days	≥ 27 N/mm ²
Water absorption after 240 min	≤ 3.5 g
Operating temperature	From -40°C to +90°C

Application Information

Grouting from 3 to 12 mm, of high strength, with low water absorption and extremely fine finishing. Suitable for grouting grès porcelain stoneware, low thickness slabs, all types of ceramic tiles, clinker, terracotta, glass mosaic and ceramic of any type and format.

Natural stone, marble, etc. Floors and walls, indoor and outdoor of normal use, commercial and industrial, heavy traffic environments, swimming pools and fountains, and areas subject to sudden changes in temperature.

Application Instruction

1. Mix mechanically with clean water until you obtain a smooth paste of the required consistency.
2. Check that joints are clean and free from any dust or adhesive. Leave to stand for 2 - 5 minutes before applying.
3. Moisten the application surface if weather conditions require it.
4. Apply with a rubber trowel in a diagonal direction to completely fill the joint. Remove immediately most of the remaining grout leaving only a thin film on the tile.

5. Carry out the finishing process once the top of the mortar has started to harden.
6. Start cleaning work as soon as the grout has thickened. For the final cleaning, use a dampened sponge with clean water, thick enough and large dimensions to avoid undermining the joints.

Available Formats

CAPAGEL FLEX COLOR 3-12 is available in 5 kg plastic bags in boxes of 20 kg, dispatched on shrink wrapping pallets weighing a total of 800 kg (40 boxes).

Warnings And Recommendations

- Do not apply when frost or rain are forecasted.
- Do not apply at temperatures below 5°C or above 35°C.
- In extreme weather conditions (strong winds or high temperatures), drying is faster than usual, causing a reduction in the open time of the application.
- In high temperatures, windy conditions or if the application is very absorbent, it is advisable to moisten the surface and wait for the film of water to disappear before applying the product.
- Check the suitability of the product depending on the type of water and the intended physical or chemical treatment.
- Grouting on still damp surfaces can cause variations in the joints.
- Clean the joint placed by using a dampened sponge in order to hydrate it.
- Retouch the product several times with a trowel for a good penetration.
- In case of thicknesses exceeding 12 mm, mix with aplica Latex.
- Protect the product from direct rain and sunlight for at least 12 h after application.
- Use within 1 year of date of packaging. Store the product in its original packaging in a dry, covered place protected from humidity.

Warranty

Topkrete Sdn Bhd warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to TOPKRETE SDN BHD shall be limited to replacement of the material proven to be defective, and TOPKRETE SDN BHD shall in no case be liable otherwise or for incidental or consequential damages. **TOPKRETE SDN BHD MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.** User shall determine the suitability of the product for its intended use and assume all risks and liability in connection therewith.

Important note

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.

Malaysia Office: Topkrete Sdn Bhd (597943-M)
19-G, Blok A, Jalan Atmosphere 3,
Pusat Perniagaan Atmosphere,
Bandar Putra Permai,
43300 Seri Kembangan,
Selangor Darul Ehsan, Malaysia
Tel: +603- 8957 8999 Fax: +603-8959 1661
Email: info@topkrete.com
www.topkrete.com

Spain Office: Cementos CAPA, S.L
Muelle de Ribera-Poniente, s/n.
Puerto de Almeria, 04002 Almeria
(Espana/Spain/Espagne/Espanha)
T: + (34) 950 620 620
www.capa.es

Technology from



Spain